



Registration Certificate

Carpet Name: E616

Licensee: INTERFACE

Licence Number: 1016

Label Number: 24334

ACCS Contract Grading: CHD 3*

ACCS Residential Grading: NONE

Suitable for Stairs: Yes

Date Graded: 21-02-2024



Andrew Martin
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 3004 Tel: (03) 9804 5559

Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details:

Company: INTERFACE

Label No: 24334

Licence No: 1016

Office No: 7513

Names:

E616

Details:

Awarded Res Grade: NONE
 Awarded Con Grade: CHD 3*
 Registered On: 21/02/2024
 Active: Yes
 Date In-Active:
 Manufacture Method: Tufted
 Twist Set: N/A
 Dyeing Method: Melt Dyed
 #Colours/Designs: 12/
 Backing Type: Other
 Felted: N/A
 Spinning System: BCF
 Insect Resist Agent: N/A
 Filament: 23.81
 Master Product:

Test Results:

Pile Mass g/m² (oz/yd²): 610 (18.0)
 SPM g/m² (oz/yd²): 395.36(11.7)
 Stated Pile Height (mm): 3.0
 Minimum Pile Height (mm): 2.7
 Maximum Pile Height (mm): 3.3
 Dynamic Loading Loss (%): 0.0
 Static Loading Loss (%): 0.0
 Tex (g/1000m): 300
 Measured Pile Thickness (mm): 2.9
 Machine Gauge (Tufts/dm): 47.0
 Meas Tufts Perp to Selvedge: 48.0
 Meas Tufts Para to Selvedge: 32.0
 Treated For Soiling Resistance: No
 Soil Resist Inhibitor: No
 Stain Resist Inhibitor: No

Hexapod Scores:

	Texture		Colour		Thickness	
	WA		WA		(mm)	(%)
1500:	3.5	0.0	4.0	0.0	0.3	10.0
8000:	2.5	0.0	2.5	0.0	0.8	26.7

Quality Assurance Test:

Cut Pile (%): 0
 Loop Pile (%): 100
 Panel Assessment Contract: 13
 Panel Assessment Residential: 13
 Suitable For Stairs: Yes
 Tile: Yes SheetGoods: No
 Fibre Signature: NBA:100

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	13.4	16	16
Volume Density:	12	12	20
Tuft Density:	7.5	7.5	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	12	12	14
Abrasion Res:	10	10	10

Calculations

Pile Height(mm): 4.4
 Tuft Density(per dm²): 1536.0
 GSPM(g/m²): 397.0
 GSPM (abrasive) (g/m²): 275.0
 Soiling Propensity: 12.0 +0.0

OAF Values

OAF: 4.2
 Calc Density (+-5%):0.13 0.136 0.14
 Base Fibre: NYLON
 Benchmarks:
 RHD1 0 RHD2 3.5
 REHD1 3.5 REHD2 3.5

Environmental Classification:

ECS:

Level:

	Calc	B/M	P/F
Acoustic:	2.9	3	
Thermal:	21.3	15	PASS
VOC:			
TVOC	0		

Notes:

16/02/2024 - Submitted by Alison Attenborough. 21/02/2024 Panel graded as CHD(S) 3*.